



FGS-0125

Tech Index:

ITEMS	UNITE	STANDARD	DATA
Carbon content	%	≥98	99.5
Thickness tolerance	mm	0.125±0.03	0.125±0.015
Density tolerance	g/cm ³	1.5±0.05	1.5±0.05
Sulphur content	PPM	≤1200	800
Thermal conductivity through plane	W/MK	600 (for reference only)	
Thermal conductivity through thickness	W/MK	6 (for reference only)	
Remark	According : JB/T 7758.2-2005, ASTM D5470		

AMEC Thermasol

1-2 Steam Mill Lane, Great Yarmouth, Norfolk, NR31 0HP

Telephone: +44(0) 1493 668622

Fax: +44(0) 1493 668623

Email: sales@amecthermasol.co.uk

Website: www.amecthermasol.co.uk