


THERMAL FILLER PAD

6.0W/mK, 80 SHORE 00, 305x305x0.3~3.0Tmm

W10TR600A

With an extremely high thermal conductivity 6.0 (W/m-K); medium softness 80 Shore 00; with high tensile strength. The W10TR600A thermal conductive filler pad is a good general purpose, competitively priced, material. The thermal gap filler provides durability in harsh environments whilst conducting heat away from electronic components. Available with adhesive tape one side or both sides and with one. Can be supplied die cut to customer specification.



PRODUCT APPLICATION

- Electronic parts: IC, CPU, MOS.
- LED, M/B, PS, HEAT SINK, LCD-TV, NB.
- DDRII Module, DVD Application and so on.

Item	Unit	W10TR600A	Test Method			
Thermal Conductivity	W/m.k	6.0	ASTM D5470			
Hardness	Shore 00	80	ASTM D2240			
Thickness	mm	0.3 ~ 3.0	ASTM D374			
Specific Gravity	g/cm ³	2.46	ASTM D792			
Weight Loss	%	<1	120° / 24hrs			
Tensile Strength	Psi	35	ASTM D412			
Elongation	%	140	ASTM D412			
Insulation Strength	kV / mm	10	ASTM D149			
Flammability	-	94 V-0	UL			
Max Temperature Range	°C	-40~+200	-			
Sheet Size	mm	305x305	-			
Colour	-	Grey	Visual			
Thermal Resistance						
Thickness	0.5mm	1.0mm	1.5mm	2.0mm	3.0mm	5.0mm
°C/W	0.167	0.398	0.540	0.610	0.896	N/A
°C*cm ² /W	1.604	3.822	5.189	5.860	8.612	N/A
°C*in ² /W	0.249	0.593	0.804	0.908	1.335	N/A
Specimen : 31mm-square (@40 psi)						

Part number system:

W10TR600A-XX-TX

XX = Thickness
05 - 0.5mm
10 - 1.0mm
20 - 2.0mm
30 - 3.0mm

GF = One side Fiberglass reinforcement
Blank – Not required

TX = Adhesive Tape
T1 - One side
T2 - Two Side

AMEC Thermasol

1-2 Steam Mill Lane, Great Yarmouth, Norfolk, NR31 0HP

Telephone: +44(0) 1493 668622 Fax: +44(0) 1493 668623

Email: sales@amecthermasol.co.uk Website: www.amecthermasol.co.uk